# PRODUCT DATA SHEET





AMBI-TITE 204 (HFO) Product Data Sheet Revised 05/07/2025

## **DESCRIPTION**

AMBI-TITE 204 (HFO) is a rigid polyurethane spray foam insulation. The controlled chemical reaction allows for smoother surface and more uniform application over a wide temperature range.

AMBI-TITE 204 (HFO) uses zero ozone depleting potential (ODP) blowing agents.

AMBI-TITE 204 (HFO) shows excellent adhesion to a wide range of substrates typically found in a building construction, as well as air seals and insulates one step.

AMBI-TITE 204 (HFO) meets the intent of the building codes for residential and commercial construction.

## **REACTION-TO-FIRE**

PROPERTY	TEST METHOD	PRELIMINARY VALUE
Surface Burning		Class 1
Characteristics	ASTM E84	Flame Spread <25
		Smoke Developed <450
Thermal Barrier		DC 315 @14 wet mils/9 dry
Compliant 2018, 2021		mils: PASS
IBS & IRS as an interior	NFPA 286	Fireshell F10E @18 wet mils
finish without a 15-		12 dry mils: PASS
minute thermal barrier.		Flame Control @14 wet mils
		9 dry mils: <b>PASS</b>
		No-Burn Plus ThB @14 mils
		9 dry mils: <b>PASS</b>

The flammability rating stated in this document is not intended to reflect hazards under actual fire conditions. These ratings are used soley to measure and describe the products response to heat and flame under controlled laboratory conditions.

PHYSICAL PROPERTIES			RECOMMENDED PROCESSING PARAMETERS			
<b>PROPERTY</b>	<b>TEST METHOD</b>		RESULTS		SUMMER BLEND	WINTER BLEND
Density	ASTM D1622	2.0 lbs.ft <sup>3</sup>		Primary A-Side Heater	108° - 115° F	108° - 130° F
Thermal Resistance				Primary B-Side Heater	108° - 115° F	108° - 130°F
Resistance	ASTM C518	Initial	6.8 (°F.ft2h/Btu)	Hose Temperature	108° - 115° F	108° - 130° F
@ 1 inch				Processing Pressure	900 - 1200 psi	900 - 1200 psi
Compressive ASTM 1621 Strength	>20 psi		Minimum Application	>50° F	>20° F	
			Ambient Humidity	<85%	<85%	
Air Permeance	ASTM 2178	<0.02L/sn	1 <sup>2</sup>	Maximum Moisture of Wood Substrate	19%	19%
Tensile Strength	ASTM 1623	27 psi		This product should only b	e applied by trained ap	plicators using 1:1 by volume
Open Cell Content	ASTM 6226	<10%		proportioning equipment capable of maintaining the pressures and temperatures as recommended by AMBIT Polyurethane. Like all isocyanate		
Dimensional Stability (Aging 7 days)	ASTM 2126	<10%		based foams, the chemical reaction varies significantly due to the equipment, environmental conditions, and applicator technique. Applicators should monitor the chemical temperature, pressures and the rate of rising foam to		
		Class	II Vapor Retarder In	obtain the best yield for op	timum performance. P	Prior to spraying, maintain the

Accordance with IBC

Water Vapor ASTM E96 @ 1inch 0.94 Perms Permeance PROCEDURE A

■Protect from sunlight

guns can be used with this chemical system.

•Substrate should be free from oils, grease, frost, water or materials which could affect

chemical temperature inside the drums at 70° - 80° F. Air or mechanical purge

# LIQUID COMPONENT PROPERTIES

FIGUID COLLICIT	EITH I NOI EITHE	•
PROPERTY	AMBIT PMDI-ISO ISOCYANATE (A-COMPONENT)	AMBI-TITE 204 (HFO) RESIN (B-COMPONENT)
Color	Dark Brown	Transparent Yellow
Viscosity @ 75%	150-250 cps	300 - 450 cps
Specific Gravity	1.22 - 1.24	1.11 - 1.15
Storage Temperature	65° - 110°F	55° - 70° F
Shelf Life	One Year (12 months)	Six Months (6 months)
Volumetric Mixing Ratio	100:100	100:100

AMBITPU.COM

#### **FIRE SAFETY**

The combination of the A&B components create a chemical reaction that produces heat. Applicators should limit the application of this product to no more than a thickness of 4" per pass (after expansion) to avoid a fire hazard (including spontaneous combustion) resulting from excessive heat •Contain and cover spilled material with absorbent materials. generation. If subsequent passes are needed, applicators should wait until the core temperature of the foam has dropped below 100° F to allow any reaction heat to dissipate from the prior applications before attempting to reapply the product. The polyurethane foam produced from •Wash the contaminated areas thoroughly. this resin is combustible. Do not expose to open flame, welding torches, sparks, etc. Keep the foam at least 3 inches (76 mm) away from heat producing sources. No smoking during product application.

#### SPILLS AND LEAKS

- ■Ventilate area to remove vapors and use personal protective equipment
- ■Report spills more than 5,000 lbs. to environmental agencies.

#### RESPIRATORY PROTECTION

AMBIT Polyurethane requires a full-face mask with supplied air to be used during the application of our spray foam systems. A copy of the Model Respiratory Protection Program developed by CPI can be obtained from AMBIT or by visiting www.polyurethane.org. Read the Safety Data Sheets (SDS for additional information on safe use and handling.



## **MANUFACTURED BY**

### AMBIT POLYURETHANE LLC.

2925 Galleria Drive · Arlington, TX 76011 (817) 677-1200 · Info@AmbitPU.com

#### **DISCLAIMER:**

To the best of our knowledge, all technical data contained herin is true and accurate as of the date of issuance and subject to change without prior notice. User may contact AMBIT Polyurethane to verify correctness before specifying or ordering. We guarantee our products to conform to the quality control standards established by AMBIT Polyurethane. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY AMBIT POLYURETHANE EXPRESSED OR IMPLIED, STATUTORY, BY OPERATIONOF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. ALL PATNET RIGHTS ARE RESERVED.